

*Gel Strong Acid Cation Resin*

Purolite C100 is supplied in the sodium form and it is primarily used in coflow regenerated industrial softening or when regenerated with mineral acids (hydrochloric or sulfuric acids) as the cation resin in demineralization plants used in industrial water treatment. This premium gel product has been optimized to give a high working capacity and good kinetic performance across a wide range of operating conditions while offering excellent chemical and physical stability.

This product is also available in special grades which offer improved performance in both coflow regenerated plant and in a wide range of counterflow regenerated systems. Special grades are also available for use in other cation resin applications. The expected performance is demonstrated in the Purolite PureDesign Program and this product is also available in the hydrogen form as Purolite C100H

**Typical Physical and Chemical Characteristics**

**BASIC FEATURES:**

**Application** - Softening and Demineralization - supplied in Na<sup>+</sup> form

**Polymer Structure** - Gel polystyrene crosslinked with DVB

**Appearance** - Amber, clear spherical beads

**Functional Group** - Sulfonic acid

**Ionic Form as Shipped** - Na<sup>+</sup>

**PRODUCT INFORMATION:**

Total Capacity, Na <sup>+</sup> Form (min.)	2.0 eq/l (43.7 Kgr/ft <sup>3</sup> )
Moisture Retention, Na <sup>+</sup> Form	44 - 48%
Particle Size Range	300-1200 µm
<300 µm (max.)	1%
Uniformity Coefficient (max.)	1.7
Reversible Swelling, Na <sup>+</sup> → H <sup>+</sup> (max.)	8%
Specific Gravity	1.29 (Na+form)
Shipping Weight (approx.)	800 - 840 g/l (49.9 - 52.4 lbs/ft <sup>3</sup> )
Temperature Limit	120 °C (250 °F)

**USA**

Telephone: +1 610 668 9090  
Fax: +1 610 668 8139  
Email: [info@puroliteusa.com](mailto:info@puroliteusa.com)

**Europe**

Telephone: +44 1443 229334  
Fax: +44 1443 227073  
Email: [sales@purolite.com](mailto:sales@purolite.com)

**Asia Pacific**

Telephone: +86 571 876 31385  
Fax: +86 571 876 31385  
Email: [pultalan@purolitechina.com](mailto:pultalan@purolitechina.com)